

LAMPIRAN

LAMPIRAN

No.Sampel	Variasi	Serbuk kayu (%)	Umur	Berat (kg)	Kuat tekan (Mpa)	Kuat tekan kg/cm2
A1	1	0	7 hari	530.40	10.86	110.75
A2		0	7 hari	471.80	6.66	67.90
A3		0	7 hari	502.95	9.26	94.42
A4		0	14 hari	466.30	7.64	77.90
A5		0	14 hari	493.40	7.22	73.66
A6		0	14 hari	480.10	7.48	76.27
A7		0	21 hari	486,10	14,16	144,39
A8		0	21 hari	492.40	14.74	150.35
A9		0	21 hari	478.40	13.19	134.55
A10		0	28 hari	475.34	16.65	169.75
A11		0	28 hari	453.26	14.91	152.04
A12		0	28 hari	429.38	13.59	138.53
B1	2	3	7 hari	434.60	9.51	97.00
B2		3	7 hari	449.35	10.42	106.25
B3		3	7 hari	461.40	11.06	112.76
B4		3	14 hari	472.70	6.96	70.93
B5		3	14 hari	473.50	10.97	111.85
B6		3	14 hari	474.30	8.40	85.68
B7		3	21 hari	426.00	10.81	110.23
B8		3	21 hari	417.25	12.09	123.28
B9		3	21 hari	406.50	13.12	133.83
B10		3	28 hari	429.45	16.86	171.92
B11		3	28 hari	440.19	17.06	173.96
B12		3	28 hari	416.61	16.52	168.44
C1	3	6	7 hari	413.75	6.85	69.85
C2		6	7 hari	409.00	6.93	70.62
C3		6	7 hari	417.50	6.71	68.42
C4		6	14 hari	440.70	8.40	85.68
C5		6	14 hari	427.35	7.12	72.60
C6		6	14 hari	414.10	5.56	56.68
C7		6	21 hari	419.15	9.71	99.01
C8		6	21 hari	427.50	11.79	120.21
C9		6	21 hari	410.20	7.44	75.85
C10		6	28 hari	396.51	13.17	134.29
C11		6	28 hari	386.82	10.25	104.51
C12		6	28 hari	392.15	11.83	120.63
D1	4	9	7 hari	398.50	5.02	51.16
D2		9	7 hari	386.60	3.32	33.90
		9	7 hari	391.65	4.27	43.54
D3		9	14 hari	394.90	2.37	24.17
D4		9	14 hari	376.70	2.86	29.19
		9	14 hari	384.30	2.65	26.78
D5		9	21 hari	359.80	3.17	32.36
D6		9	21 hari	396.60	4.05	41.30
		9	21 hari	379.40	3.71	37.83
D7		9	28 hari	390.10	11.48	117.06
		9	28 hari	371.14	7.64	77.56
D8		9	28 hari	351.78	3.70	37.72

**Foto Dokumentasi****Penimbangan Benda Uji *Paving Block***





### Pengujian Kuat tekan paving block











